NOTES:

- 1. SUBSTRATE: GRADE A FINE ANNEALED SCHOTT: N-BK7 517/642
- ROHS COMPLIANT
- 3. SURFACE S2 TO BE PARALLEL TO SURFACE S1 TO WITHIN 3 ARCMIN
- 4. COATING (APPLY ACROSS COATING APERTURE)
 SPECIFICATIONS AT 45° AOI AND RANDOM POLARIZATION
 \$1:

 $R(abs) = 70\% \pm 5\% @ 550nm$ $R(abs) = 70\% \pm 10\% FROM 400-700nm$

T(abs) = 30% ±15% @ 550nm T(abs) = 30% ±10% FROM 400-700nm VISUAL COLOR = NEUTRAL

S2: BBAR


 $R(abs) \le 2.0\%$ FROM 400-700nm $R(avg) \le 1.0\%$ FROM 400-700nm

5.

FINE GRIND SURFACE



MARK IDENTIFIES BEAMSPLITTER SURFACE



FOR INFORMATION ONLY: DO NOT MANUFACTURE PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

	\$1	\$2	
SHAPE	PLANO	PLANO	
SURFACE FLATNESS	1λ PER 25mm	1λ PER 25mm	
SURFACE QUALITY	60 - 40	60 - 40	
MIN CLEAR APERTURE	63.75 x 63.75	63.75 x 63.75	
MIN COATING APERTURE	63.75 x 63.75	63.75 x 63.75	
BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED	

			Edmund Optic		CS [®]
THIRD ANGLE PROJECTION		TITLE	BS VIS 70R/30T 75X75MM 1MM THK		
	ALL DIMS IN	mm	DWG NO	35957	SHEET 1 OF 1